


12V 9Ah - MBESL104 - AGM Battery



The battery is constructed by plates, separators, safety valves and container. Since the electrolyte is held by a glass mat separator and plates, the battery can use in any direction and position without leakage.

Performance Characteristics

Nominal Voltage	12V
Number of cell	6
Life (Year)	5 years
Nominal Capacity 77°F(25°C)	
20-hour rate (0.45A,10.5V)	9Ah
10-hour rate (0.84A,10.5V)	8.4Ah
5-hour rate (1.53 A,10.5V)	7.65Ah
1-hour rate (5.85A,9.6V)	5.85Ah
Internal Resistance	
Fully Charged battery 77°F(25°C)	30 mΩ
Self-Discharge	
3% of capacity declined per month at 20°C(average)	
Operation Temperature Range	
Discharge	-20~60°C
Charge	-10~60°C
Storage	-20~60°C
Max.Discharge Current 77°F(25°C)	135A(5s)
Short Circuit Current	540A



Dimensions and Weight (+/- 2mm)

Length (mm / inch)	151 / 5.94
Width (mm / inch)	65 / 2.56
Height (mm / inch)	94 / 3.70
Total Height (mm / inch)	99 / 3.90
Approx. Weight (Kg / lbs)	2.50 / 5.50

Discharge Constant Current (Amperes at 77°F25°C)

F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
9.60V	31.5	25.2	18.0	10.4	7.38	5.85	3.15	2.28	1.55	1.02	0.85	0.46
9.90V	30.6	24.3	17.1	10.2	7.29	5.81	3.12	2.27	1.54	1.02	0.85	0.46
10.20V	28.8	22.5	16.2	9.90	7.20	5.76	3.11	2.25	1.53	1.01	0.84	0.45
10.50V	25.2	18.9	15.3	9.36	7.11	5.67	3.06	2.22	1.53	1.00	0.84	0.45
10.80V	22.5	16.2	14.4	8.10	7.02	5.58	2.97	2.16	1.51	1.00	0.82	0.44

Discharge Constant Power (Watts at 77°F25°C)

F.V/Time	5min	10min	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h
9.60V	344	276	199	120	84	67.5	36.3	26.3	17.9	11.8	9.9	5.40
9.90V	330	265	188	116	83	66.4	36.1	26.2	17.8	11.8	9.8	5.40
10.20V	314	249	179	111	82	66.4	35.8	26.1	17.7	11.8	9.8	5.34
10.50V	275	210	169	104	81.0	65.3	35.3	25.7	17.7	11.6	9.7	5.22
10.80V	246	189	159	90.2	79.9	64.3	34.2	25.0	17.6	11.6	9.5	5.16









Battery Construction

COMPONENT	Positive	Negative	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
RAW MATERIAL	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

Charging Methods

Application	Charging method	Charging Voltage at 25° C	Temperature compensation coefficient of charging voltage	Max. charging current	Charging time 25°C(h)		Temp (° C)
					100% discharge	50% discharge	
For standby power source	Constant voltage & Constant Current	13.4-13.8V	-20 mV/° C	2.7A	24	20	0~40 (32~104° F)
For cycle service	Charging (with current restriction)	14.5-15.0V	-30 mV/° C	2.7A	16	10	

*Temperature compensation of charging voltage is not needed. When using the batteries within 15° C to 35° C range.



Braga Moro Offices

Braga Moro Headquarters

Via San Gregorio 12,
20124 Milan
Italy.
www.bragamoro.com

Braga Moro Sales Office

Via Ludwig Van Beethoven 24,
20092 Cinisello Balsamo. Milan.
Italy.
Tel: +39 02 51 67 22 01
Fax: +39 02 51 67 22 13
E-mail: sale@brgamoro.com

Braga Moro Office

Via Tenuta Piccirilli, 104
00188, Roma, RM
Italy.